

IN THE CLAIMS

The following claim set replaces all prior versions, and listings, of claims in the application:

B¹
1. (Previously Amended) A heat-resistant glass fiber which has a composition comprising, by weight %, 56 to 58.5% of SiO₂, 12 to 17% of Al₂O₃, 16 to 27% of CaO, 1 to 9% of MgO, 0 to 1% of Na₂O and 0 to 1% of K₂O as the entirety of the fiber and containing neither B₂O₃ nor F₂, and which has a surface layer portion made of a silicic glass having an SiO₂ content of at least 90% by weight.

2. (Original) The heat-resistant glass fiber of claim 1, wherein the surface layer portion made of a silicic glass having an SiO₂ content of at least 90% by weight has a thickness of 0.1 to 1.0 μm.

3. (Original) The heat-resistant glass fiber of claim 1, wherein a difference ΔT between a spinning temperature which is a melting temperature of a glass having a viscosity of 100 Pa·s and a liquidus temperature is at least 30°C.

4. (Original) A process for the production of the heat-resistant glass fiber recited in claim 1, which comprises treating the surface of a glass fiber which has a composition comprising, by weight %, 56 to 58.5% of SiO₂, 12 to 17% of Al₂O₃, 16 to 27% of CaO, 1 to 9% of MgO, 0 to 1% of Na₂O and 0 to 1% of K₂O and containing neither B₂O₃ nor F₂, with a mineral acid.

5. (Original) The process of claim 4, wherein the treatment is carried out by immersing the glass fiber in an aqueous solution containing, as the mineral acid, 1 to 10%

by weight of at least one acid selected from HCl, H₂SO₄ or HNO₃ at a temperature of 0 to 90°C.

B1
(md) 6. (New) A heat-resistant glass fiber which has a surface layer portion at least 0.01 μm thick, made of silicic glass having an SiO₂ content of at least 90%, the balance of the glass fiber having a composition comprising by weight %, 56 to 58.5% of SiO₂, 12 to 17% of Al₂O₃, 16 to 27% of CaO, 1 to 9% of MgO, 0 to 1% of Na₂O and 0 to 1% of K₂O as the entirety of the fiber and containing neither B₂O₃ nor F₂.
